

# Electrodynamics of $\text{Nd}_{0.7}\text{Sr}_{0.3}\text{MnO}_3$ Single Crystal investigated by Optical Conductivity Analyses

H. J. Lee, J. H. Jung, Y. S. Lee, J. S. Ahn, and T. W. Noh

*Department of Physics and Condensed Matter Research Institute,  
Seoul National University, Seoul 151-742, Korea*

K. H. Kim

*Department of Physics and Astronomy, Rutgers University, Piscataway, NJ 08855*

S-W. Cheong

*Department of Physics and Astronomy, Rutgers University, Piscataway, NJ 08855  
and Bell laboratories, Lucent Technologies, Murray Hill, NJ 07974*

(February 1, 2008)

## Abstract

We investigated temperature dependent optical conductivity spectra of  $\text{Nd}_{0.7}\text{Sr}_{0.3}\text{MnO}_3$  *single crystal*. We found that polishing and surface scattering effects on the  $\text{Nd}_{0.7}\text{Sr}_{0.3}\text{MnO}_3$  crystal surfaces could significantly distort the optical responses, especially in the mid-infrared region. However, oxygen annealing and gold normalization processes seemed to remedy the distortions. We found that the spectral weight of  $\text{Nd}_{0.7}\text{Sr}_{0.3}\text{MnO}_3$  in the metallic state might be composed of a Drude carrier term and a strong incoherent mid-infrared absorptions. The temperature dependence of the spectral weight suggests that the electron-lattice coupling should be important in op-

tical properties of colossal magnetoresistance manganites.

PACS numbers: 71.30.+h, 75.50.Cc, 78.20.Ci

## I. INTRODUCTION

It has been well known that series of doped manganites with the chemical formula  $R_{1-x}A_x\text{MnO}_3$  ( $R = \text{La}$  or  $\text{Nd}$ , and  $A = \text{Ca}$ ,  $\text{Sr}$ , or  $\text{Ba}$ ) near  $x \sim 0.3$  undergo paramagnetic insulator to ferromagnetic metal transitions and show colossal magnetoresistance (CMR) phenomena near the transitions. The coexistence of metallicity and ferromagnetism in manganites has been explained by the double exchange (DE) interaction with a strong Hund coupling between  $e_g$  carrier and  $t_{2g}$  spins. However, it has been argued that some additional degrees of freedom, such as lattice,<sup>1</sup> orbital,<sup>2</sup> and disorder<sup>3</sup>, should be included to explain the CMR quantitatively.

Optical measurements have been very useful to investigate the basic mechanisms of some insulator-metal transitions and associated electronic structure changes.<sup>4-7</sup> There have been numerous optical investigations on manganites, however, the experimental data and their interpretations are varied. Especially, there are several different views on the electrodynamic responses in the metallic states.

One of such difficulties comes from sample preparation methods. For examples, Okimoto *et al.*<sup>4</sup> investigated optical responses of polished (La,Sr)MnO<sub>3</sub> single crystals and reported a small Drude weight in the metallic state. Later, Takenaka *et al.*<sup>5</sup> showed that cleaved (La,Sr)MnO<sub>3</sub> single crystals had optical spectra different from those of the polished crystals, and claimed that the small Drude weight in the polished samples should be originated from damaged surfaces during the polishing process. The problem due to the sample preparation method is more serious for Nd<sub>0.7</sub>Sr<sub>0.3</sub>MnO<sub>3</sub> thin films. Kaplan *et al.*<sup>6</sup> reported an optical response of Nd<sub>0.7</sub>Sr<sub>0.3</sub>MnO<sub>3</sub> thin film. They could not observe the Drude-like peak even in the metallic region at low temperature. Later, Quijada *et al.*<sup>8</sup> reported a Drude-like free carrier behavior for an oxygen-annealed Nd<sub>0.7</sub>Sr<sub>0.3</sub>MnO<sub>3</sub> film. Therefore, careful surface treatments and exact optical measurements are inevitable to get correct electrodynamical responses and to understand the basic mechanism of the CMR.

In this paper, we present optical conductivity spectra  $\sigma(\omega)$  of Nd<sub>0.7</sub>Sr<sub>0.3</sub>MnO<sub>3</sub> (NSMO)

*single crystal* for annealed and polished surfaces. Although *dc* conductivity values of the both surfaces were nearly the same, their  $\sigma(\omega)$  were quite different. Using the oxygen annealing and gold the normalization techniques, surface strain and surface scattering effects could be removed. Our experimental data suggested that the low frequency spectral weight in the metallic states might be composed of a Drude part and a strong incoherent mid-infrared absorptions. The temperature dependence of the spectral weight supports that lattice effects are important in NSMO.

## II. EXPERIMENTAL

The NSMO single crystal was prepared by floating zone methods. Details of crystal growth and characterizations were described elsewhere.<sup>9</sup> Just before optical measurements, the sample was polished up to  $0.3\ \mu\text{m}$  using diamond pastes. After the polishing, we carefully annealed the sample again in an  $\text{O}_2$  atmosphere at  $1000\ ^\circ\text{C}$  for 1 hour. Figure 1 shows values of temperature ( $T$ )-dependent dc resistivity  $\rho(T)$  of our NSMO single crystal, which were measured by the conventional four-probe method. The solid and the dashed lines represent the  $\rho(T)$  curves of the polished and the annealed NSMO, respectively. The  $\rho(T)$  curves show a typical insulator-metal transition around 198 K. It seems that overall features of  $\rho(T)$  for the polished and the annealed NSMO are nearly the same except for small deviations around  $T_C$ . Although such an annealing procedure does not change  $\rho(T)$  significantly, it seems to be very important for optical properties of the NSMO sample. As demonstrated in the next section, optical properties of the NSMO crystal became changed drastically after the oxygen annealing.

Near normal incident reflectivity spectra,  $R(\omega)$ , were measured in a wide photon energy region of  $5\ \text{meV} \sim 30\ \text{eV}$  and at temperatures between 15 and 300 K. We used a conventional Fourier transform spectrophotometer between 5 meV and 0.8 eV. Above 0.6 eV, grating spectrometers were used. Especially above 6.0 eV, we used the synchrotron radiation from the Normal Incidence Monochromator beam line at Pohang Light Source (PLS).  $T$ -dependent

$R(\omega)$  below 6.5 eV were measured using a liquid He-cooled cryostat. To subtract surface scattering effects from  $R(\omega)$ , we used the gold normalization technique<sup>10</sup>: a gold film was evaporated onto the sample surface just after spectra were taken. Then, the reflectivity of the gold coated surface was measured and used for normalizing  $R(\omega)$  of the NSMO sample.

Using the Kramers-Kronig (KK) analysis with the normalized  $R(\omega)$ , we obtained  $\sigma(\omega)$ . For this analysis,  $R(\omega)$  in the low frequency region were extrapolated with the Hagen-Rubens relation<sup>11</sup> for metallic states and with constants for insulating states. To obtain accurate  $\sigma(\omega)$  in the far-infrared region, we also compared  $R(\omega)$  extrapolated using the Hagen-Rubens relation with those extrapolated using the Drude model, and we obtained nearly the same results in the far-infrared region. The  $T$ -dependent  $R(\omega)$  spectra below 6.5 eV were smoothly connected with the reflectivity data obtained at room temperature from 6.0 to 30 eV, assuming that reflectivity in the high energy region should be nearly temperature independent. For the frequency region above our measurements, the reflectivity at 30 eV was extended up to 40 eV and then  $\omega^{-4}$  dependence was assumed. Using spectroscopic ellipsometry (SE), we obtained  $\sigma(\omega)$  in the region of 1.5  $\sim$  5.0 eV without relying on the KK extrapolation. The  $\sigma(\omega)$  obtained by the SE method were quite consistent with those by the KK analysis. This fact suggests validity of our gold normalization techniques and the extrapolations used in the KK analysis.

### III. RESULTS AND DISCUSSION

#### A. Effects of Oxygen Annealing

Although the oxygen annealing process does not change  $\rho(T)$  very much, it affects the optical responses of NSMO significantly. Fig. 2(a) shows  $R(\omega)$  for the polished and the annealed surfaces of the NSMO single crystal. [Note that both of these spectra were corrected by the gold normalization technique, so differences are mainly due to the oxygen annealing effects.] In the insulating region above  $T_C$ , the differences in  $R(\omega)$  are not significant.

However, in the metallic region below  $T_C$ ,  $R(\omega)$  for the polished surface are much lower in the frequency region from  $2 \times 10^{-2}$  to 1.5 eV. The dip in  $R(\omega)$ , so-called the "plasma edge", for the polished surface appears around 0.6 eV, which is much lower than the observed dip around 2.0 eV for the annealed surface. The differences in the polished and the annealed surfaces can be clearly seen in  $\sigma(\omega)$ , which are displayed in Fig. 2(b). After the annealing, the spectral weight in the infrared region becomes enhanced considerably. Although Drude-like peaks at the far-infrared region can be observed at 15 K for both surfaces,  $\sigma(\omega)$  of the polished surface has a smaller spectral weight.

Changes in the optical response due to the oxygen annealing were already noticed in NSMO thin films. Kaplan *et al.* reported that a NSMO film, whose resistivity peak temperature  $T_P$  was located around 180 K, had a strong mid-infrared peak and no Drude-like free carrier peak.<sup>6</sup> Later, the same group reported that  $T_P$  of a NSMO film became about 230 K when it was annealed in an oxygen environment.<sup>8</sup> They showed that the strength of the mid-infrared peak became weakened considerably and that the Drude-like free carrier behavior appeared in the oxygen-annealed NSMO film. We think that the optical response changes in the NSMO film were related with the dc resistivity changes reported by Xiong *et al.*<sup>12</sup> They investigated the effects of oxygen annealing in NSMO films. With more annealing, their resistivity values became smaller and  $T_P$  moved to a higher temperature. They suggested that the annealing effects in the NSMO films could be explained by a change of oxygen content and a variation of mixed  $\text{Mn}^{3+}/\text{Mn}^{4+}$  ratio.

Since  $\rho(T)$  of our NSMO single crystal does not change by the annealing process, the optical response changes observed in Fig. 2 might not come from oxygen content changes. We think that the differences in optical spectra should be originated from damages due to the polishing process. Since the electron-phonon interactions are believed to be very strong in manganites, the stress applied during the polishing process could damage the surface region and deform optical responses significantly.

## B. Effects of Gold Normalization

We also found that light scattering from the polished surface was quite severe in the NSMO sample. Figs. 3(a) and (b) show  $R(\omega)$  and  $\sigma(\omega)$  of the oxygen annealed NSMO sample at 15 K, respectively. The dashed lines are results without any correction, and the solid lines are results after the gold normalization.  $R(\omega)$  in Fig. 3(a) show that the light scattering effects are not significant below 0.1 eV, but that they become very severe between mid-infrared and visible regions. The scattering loss effects become evident in  $\sigma(\omega)$ . Fig. 3(b) shows that the spectral weight becomes reduced in most of the frequency region. Especially, the spectral change below 0.5 eV becomes quite large.

Recently, Takenaka *et al.*<sup>5</sup> compared optical reflectivity spectra of (La,Sr)MnO<sub>3</sub> cleavage surfaces with those of polished surfaces, and they showed that  $\sigma(\omega)$  of the cleaved surface have a much more enhanced Drude weight. They claimed that the damage of the polished surface should result in a serious distortion in  $\sigma(\omega)$ . Since the optical spectra of their cleaved surface [i.e. Fig. 2 of Ref. 5] are very similar to our results after the oxygen annealing and the gold normalization processes, it can be suggested that the differences observed by Takenaka *et al.* were likely to be remedied by our experimental techniques.

## C. Spectral Weight in the Insulating State

In Fig. 4, we show  $T$ -dependent  $R(\omega)$  of the annealed NSMO single crystal from 5 meV to 10 eV. At 300 K, there are three sharp peaks originated from optic phonon modes in the far-infrared region. And, broad peaks above 0.1 eV come from the optical transitions between electronic levels. With decreasing  $T$ , the value of reflectivity approaches to 1.0 in the dc limit (i.e.  $\omega \rightarrow 0$ ) and the sharp phonon features become screened by free carrier. Note that there are strong  $T$ -dependence in  $R(\omega)$  up to 5.0 eV. Similar behaviors were observed in other CMR manganites.<sup>8,13</sup>

Figure 5 shows  $T$ -dependent  $\sigma(\omega)$  of the annealed NSMO single crystal, which were

obtained by the KK analysis. In the temperature region above  $T_C$ , we can see two interesting features: an optical gap near 0.18 eV, and broad peaks around 1.2 and 4.5 eV. As  $T$  decreases, a significant amount of spectral weight between 1.0 and 5.0 eV moves to a low energy region. Above 5.0 eV, the spectral weight is nearly  $T$ -independent. Due to the similarities in peak position and strength to those of charge transfer transitions in the other manganites,<sup>13–15</sup> the peak around 4.5 eV can be assigned to a charge-transfer transition between the O  $2p$  and the Mn  $e_g$  bands. The large spectral weight change between 2.0 and 5.0 eV can be interpreted in terms of an interband transition between the Hund's rule split bands, i.e.  $e_g^\uparrow(t_{2g}^\uparrow) \rightarrow e_g^\uparrow(t_{2g}^\downarrow)$  and  $e_g^\downarrow(t_{2g}^\downarrow) \rightarrow e_g^\downarrow(t_{2g}^\uparrow)$ , in the DE picture.<sup>16,17</sup> [This notation indicates that the transitions occur between two  $e_g$  bands with the same spin but different  $t_{2g}$  spin background.] As  $T$  decreases below  $T_C$ , the spins of the  $t_{2g}$  electrons are pointing along one direction and the interband transition becomes weakened, which results in the decrease of the spectral weight.

Now, let us focus on the spectral weights in the insulating state. Although the peak near 1.2 eV appears to be one broad peak, we claim that it should be interpreted in terms of a two-peak structure: one peak is located near 1.5 eV and the other is located below 1.0 eV. For most manganites with hole concentrations below 0.4, the 1.5 eV peak could not be seen clearly. However, there have been several reports which support the existence of the 1.5 eV peak.<sup>18</sup> From doping dependent conductivity studies on (La,Ca)MnO<sub>3</sub>, Jung *et al.*<sup>14</sup> showed that such a peak should exist. Machida *et al.*<sup>19</sup> also observed similar peaks in transmission spectra of (Nd<sub>0.25</sub>Sm<sub>0.75</sub>)<sub>0.6</sub>Sr<sub>0.4</sub>MnO<sub>3</sub> and Sm<sub>0.6</sub>Sr<sub>0.4</sub>MnO<sub>3</sub> films. And, to explain optical spectra of Nd<sub>0.7</sub>Sr<sub>0.3</sub>MnO<sub>3</sub>, La<sub>0.7</sub>Ca<sub>0.3</sub>MnO<sub>3</sub>, and La<sub>0.7</sub>Sr<sub>0.3</sub>MnO<sub>3</sub> thin films, Quijada *et al.*<sup>8</sup> assumed the existence of the 1.5 eV peak.

Moreover, if the broad peak around 1.2 eV is interpreted as one optical transition related to small polaron absorption, there will be some discrepancies between the optical data and other experimental data. For examples, recent transport measurement shows that a small polaron activation energy should be about 0.15 eV,<sup>20</sup> which is smaller than 0.3 eV.<sup>21</sup> When we accept the double-peak structure, we can present a schematic diagram for the spectral weight in the insulating state, which is shown in Fig. 6(a). As shown in this diagram, there



are four main peaks below 5.0 eV: (i) a small polaron absorption peak below 1.0 eV, (ii) a peak centered around 1.5 eV, (iii) a broad peak centered around 3.5 eV, which is originated from interband transitions between the Hund's rule split bands, and (iv) a peak due to charge transfer transitions between the O 2*p* and the Mn *e<sub>g</sub>* bands.

#### D. Spectral Weight in the Metallic State

Figure 7 shows detailed  $T$ -dependent  $\sigma(\omega)$  below 2.0 eV. The solid square, triangle, and circle represent the measured dc conductivities of 15, 120, and 180 K, respectively. Above  $T_C$ , we can find three optic phonon modes. With cooling, the optic phonon modes become screened by free carrier, but their signature can be observed even at 15 K. As  $T$  decreases below  $T_C$ , the spectral features above 0.8 eV decrease, and those below 0.8 eV increase significantly. The increasing spectral weight below  $T_C$  seems to form an asymmetric band, whose peak position moves down with decreasing temperature. Even at 15 K,  $\sigma(\omega)$  seem to make a downturn around 0.1 eV, and the corresponding dc conductivity is higher by about  $1000 \text{ } \Omega^{-1}\text{cm}^{-1}$  than  $\sigma(\omega = 0.1 \text{ eV})$ . Similar spectral weight changes have been commonly observed in other manganites.<sup>8,22,23</sup>

It should be noted that reported behaviors of the broad peak structures in the low frequency regions (especially, below 0.5 eV at  $T \ll T_C$ ) are varied quite a lot in earlier works. Okimoto *et al.*<sup>4</sup> measured optical responses of (La,Sr)MnO<sub>3</sub> single crystals, and claimed that the corresponding Drude peaks are very weak and sharp. Similar behaviors were observed in La<sub>0.7</sub>Ca<sub>0.3</sub>MnO<sub>3</sub> polycrystalline samples by Kim *et al.*<sup>23</sup> However, Quijada *et al.*<sup>8</sup> investigated  $\sigma(\omega)$  of annealed Nd<sub>0.7</sub>Sr<sub>0.3</sub>MnO<sub>3</sub>, La<sub>0.7</sub>Ca<sub>0.3</sub>MnO<sub>3</sub>, and La<sub>0.7</sub>Sr<sub>0.3</sub>MnO<sub>3</sub> films on LaAlO<sub>3</sub> substrates, and observed broad and strong  $\sigma(\omega)$  features at the low frequency region. They attributed these features to Drude responses and coherent conduction. Boris *et al.*<sup>22</sup> measured  $\sigma(\omega)$  of a La<sub>0.67</sub>Ca<sub>0.33</sub>MnO<sub>3</sub> single crystal. At 78 K, its  $\sigma(\omega)$  showed a very broad Drude-like behavior which was much stronger than those of polycrystalline samples. Takenaka *et al.* also measured  $\sigma(\omega)$  of cleaved (La,Sr)MnO<sub>3</sub> single crystals, and observed

a Drude-like peak with a large spectral weight. The low temperature spectral responses observed by Quijada *et al.*<sup>8</sup> and Boris *et al.*<sup>22</sup> are similar to our  $\sigma(\omega)$  data at 15 K, displayed in Fig. 7. It demonstrates that the low frequency responses of the manganites are very sensitive to the sample preparation conditions.

One important question which we should address at this point is whether we should interpret the low-frequency broad absorption feature below 0.5 eV at 15 K as a single component Drude peak. There are three important experimental facts which we should notice. First, our experimental data showed the downturn of optical conductivity around 0.1 eV at  $T \ll T_C$ . The  $\text{La}_{0.67}\text{Ca}_{0.33}\text{MnO}_3$  single crystal data by Boris *et al.* showed the same behavior. And, the thin film data by Quijada *et al.* showed similar trends, although such behaviors were neglected by the authors since the downturn regions were close to the low-frequency infrared cutoff of  $\text{LaAlO}_3$  substrates. Second, the spectral weight changes of all the reported experiments, including the NSMO single crystal case displayed in Fig. 7, cannot be described by a decrease of one spectral component at a fixed frequency and an increase of a single Drude component near the zero frequency. Rather, they can be reasonably described by a continual evolution of an asymmetric peak whose position moves down as the sample changes from the insulating state to the metallic state. A similar trend was observed for the room temperature data of the cleaved  $(\text{La},\text{Sr})\text{MnO}_3$  single crystals, investigated by Takenaka *et al.* As Sr doping increased and the sample became more metallic, a spectral weight increased in the low frequency region, which could be described by a continual movement of an asymmetric peak. Third, some optical data cannot provide reasonable values for electrodynamic quantities, when a single component Drude peak is assumed. For example, the single crystalline  $\text{La}_{0.67}\text{Ca}_{0.33}\text{MnO}_3$  data at 78 K indicate mean free path  $l = 3.9 \sim 5.2 \text{ \AA}$ , which is comparable to the lattice constant  $a$ . This value is rather too small for metallic conduction.<sup>24</sup> On the other hand, assuming the two components response for  $\text{La}_{0.7}\text{Ca}_{0.3}\text{MnO}_3$  polycrystals, Kim *et al.*<sup>23</sup> reported that  $l \sim 25 \text{ \AA}$  at 15 K and that  $l$  becomes about  $4.2 \text{ \AA}$  near the metal-insulator transition temperature.

Therefore, we think that the low frequency response should be interpreted in terms of two

components, i.e. a coherent narrow Drude peak and an incoherent mid-infrared absorption band. Figure 6(b) shows a diagram of  $\sigma(\omega)$  for  $T \ll T_C$ , which takes account of the two-component contributions. Other features of the diagram are following: the peak due to the charge transfer transition is nearly  $T$ -independent. And, as temperature decreases below  $T_C$ , the transition between the Hund's rule split bands becomes weakened and the spectral weight below 1.0 eV increases significantly.

As displayed in Fig. 7, the incoherent mid-infrared absorption band is quite asymmetric and the Drude weight starts just below the characteristic phonon mode frequency. These optical features are quite consistent with coherent and incoherent absorptions of a large polaron, predicted by Emin.<sup>25</sup> From these observations, it can be argued that a crossover from small to large polaron states accompanies the insulator-metal transition in NSMO. Such a crossover from the small to the large polaron was also observed by other experiments, including Raman scattering<sup>26</sup> and pulsed PDF measurements.<sup>27</sup> In this polaron crossover scenario, the strong oxygen annealing dependence of the optical responses in the metallic states might be explained. Just after the polishing, the surface region should be damaged quite significantly, which blocks the motion of incoherent polaron motion. However, after the annealing, such stress-induced damages could be repaired. More detailed investigations are needed to clarify this scenario.

### E. Temperature Dependence of Low Energy Spectral Weight

To get a further understanding on the low energy spectral weight, we evaluated the effective number of carrier,  $N_{eff}(\omega_C)$ , below a cutoff frequency,  $\omega_C$ :

$$N_{eff}(\omega_C) = \frac{2m_e}{\pi e^2 N} \int_0^{\omega_C} \sigma(\omega') d\omega', \quad (1)$$

where  $m_e$  is a free electron mass and  $N$  represents the number of Mn atoms per unit volume. For actual estimation, the value of  $\omega_C$  was chosen to be 0.8 eV, since the low frequency spectral weight below  $\sim 0.8$  eV increases as  $T$  decreases below  $T_C$ , as displayed in Fig. 7.

Figure 8 shows the  $T$ -dependence of  $N_{eff}(0.8 \text{ eV})$ . Above  $T_C$ ,  $N_{eff}$  is nearly independent of  $T$ . As  $T$  decreases,  $N_{eff}$  shows an increasing behavior. In the simple DE picture, the spectral weight of the Drude carriers should be proportional to  $(1 + M^2)/2$ , where  $M$  is the magnetization. However, measured magnetization data show a very sharp increase near  $T_C$ , so a quantitative agreement between  $N_{eff}$  and  $(1 + M^2)/2$  could not be obtained. Recently, Kim, *et al.* investigated optical properties of  $(\text{La,Pr})_{0.7}\text{Ca}_{0.3}\text{MnO}_3$ ,<sup>28</sup> and found that all of  $N_{eff}/T_C$  data for various values of Pr concentration can be scaled with  $\gamma_{DE}(T)$ , which represents the temperature dependent DE bandwidth due to spin ordering within the DE model predicted by Kubo and Ohata.<sup>29</sup> To explain this scaling behavior, they adopted the theoretical results<sup>30</sup> based on a Hamiltonian including the DE interaction and Jahn-Teller (JT) electron-phonon coupling terms. They showed that  $N_{eff} \approx t\xi\gamma_{DE}(T)$ , where  $\xi$  is the polaronic band narrowing term. The solid line in Fig. 8 represents the predicted behavior of  $\gamma_{DE}(T)/\gamma_{DE}(0)$ , which agrees quite well with the evaluated values of  $N_{eff}(0.8 \text{ eV})$ . This agreement suggested that both the DE interaction and the JT electron-phonon coupling play important roles in NSMO.

## F. Electrodynamic Quantities

One of the important issues in barely conducting materials is to determine electrodynamic quantities, such as scattering rate  $1/\tau$ , carrier density  $n$ , and effective mass  $m^*$ . The mean free path  $l$  and dc conductivity  $\sigma$  can be written in terms of the electrodynamic quantities:

$$l = \tau\hbar(3\pi^2n)^{1/3}/m^*, \quad (2)$$

and

$$\sigma = ne^2\tau/m^*. \quad (3)$$

Assuming hole carrier conduction (i.e.  $n = 0.3$ ),  $l$  at 15 K was estimated to be about 13 Å. [When we assumed electron carrier conduction (i.e.  $n = 0.7$ ),  $l$  should be about 7 Å.]

As shown in the inset of Fig. 7, we fitted the free carrier absorption with the simple Drude model and found that  $1/\tau \sim 120 \pm 20 \text{ cm}^{-1}$  provided a reasonable fit to our low frequency data. Using this value of  $1/\tau$ , we found that  $m^*/m_e \sim 21 \pm 3$ .

Values of  $m^*$  could be estimated using other experimental techniques, such as specific heat measurements. Conduction carriers provide a  $T$ -linear term, whose coefficient  $\gamma$  can be written as  $\pi^2 k_B^2 N(E_F)/3$ , where  $k_B$  and  $N(E_F)$  are the Boltzman constant and density of states at the Fermi energy, respectively. In the free electron model, the corresponding linear coefficient  $\gamma_0$  can be written as  $(4\pi^3 m_e k_B^2 V/3h^2)(3n/\pi)^{1/3}$ , where  $h$  is the Planck's constant. Therefore,  $\gamma/\gamma_0$  should be the same as  $m^*/m_e$ . From specific heat measurements of  $\text{Nd}_{0.67}\text{Sr}_{0.33}\text{MnO}_3$ , Gordon *et al.*<sup>31</sup> reported the values of  $\gamma(T=0)$  as 25 mJ/K<sup>2</sup>mol. [Note that  $\gamma_0$  was estimated to be around 0.9 mJ/K<sup>2</sup>mol.] However, they claimed that the value of  $\gamma/\gamma_0$ , i.e. 26, was too large for the conduction carrier contribution, and that the coupling between Nd and Mn spins might enhance the value of  $\gamma$ .

Note that our estimated value of  $m^*/m_e$  for NSMO is larger than those of other manganites. From specific heat measurements, Hamilton *et al.*,<sup>32</sup> found that  $\gamma/\gamma_0$  was around 5 for  $\text{La}_{0.67}\text{Ba}_{0.33}\text{MnO}_3$  and around 8 for  $\text{La}_{0.8}\text{Ca}_{0.2}\text{MnO}_3$ . And, from optical measurements, Kim *et al.*,<sup>23</sup> reported  $m^*/m_e \sim 13$  for  $\text{La}_{0.7}\text{Ca}_{0.3}\text{MnO}_3$ . In the DE model,  $T_C$  should be proportional to an effective transfer integral  $t_{eff}$  for an electron hopping between Mn ions. And, in the tight binding calculation,  $N(E_F)$  is inversely proportional to  $t_{eff}$ . Since  $\gamma$  is proportional to  $N(E_F)$ ,  $\gamma$  should also be inversely proportional to  $t_{eff}$ . From the fact that  $T_C$  of NSMO is quite smaller than those of  $\text{La}_{0.7}\text{Ca}_{0.3}\text{MnO}_3$  and  $\text{La}_{0.67}\text{Ba}_{0.33}\text{MnO}_3$ , the large value of  $m^*$  in NSMO seems to be reasonable. This also supports the validity of our analysis for the NSMO metallic state in terms of a small Drude weight and a strong incoherent peak.

#### IV. CONCLUSION

We investigated the temperature dependent optical conductivity spectra of  $\text{Nd}_{0.7}\text{Sr}_{0.3}\text{MnO}_3$  single crystal. We found that the polishing process could damage the surface

region of the crystal and deform the optical spectra quite significantly. Using the oxygen annealing process and the gold normalization technique, such a damage due to the polishing process seems to be recovered. Based on optical conductivity spectra, we provided schematic diagrams for spectral weight distributions in the metallic and the insulating regions. We found that the optical response in the metallic region should be interpreted in terms of a Drude part and a strong incoherent mid-infrared absorption.

## **V. ACKNOWLEDGEMENTS**

We thank to N. J. Hur, Dr. H. C. Lee, and Dr. Y. Chung for useful discussion and helpful experiments. We acknowledge the financial support by the Ministry Education through Grant No. BSRI-98-2416, by the Korea Science and Engineering Foundation through Grant No. 971-0207-024-2, and through RCDAMP of Pusan National University. Experiments at PLS were supported in part by MOST and POSCO.

## REFERENCES

- <sup>1</sup> A. J. Millis, B. I. Shraiman, and R. Mueller, Phys. Rev. Lett. **77**, 175 (1996).
- <sup>2</sup> S. Ishihara, M. Yamanaka, and N. Nagaosa, Phys. Rev. B **56**, 686 (1997).
- <sup>3</sup> L. Sheng, D. Y. Xing, D. N. Sheng, and C. S. Ting, Phys. Rev. B **56**, R7053 (1997).
- <sup>4</sup> Y. Okimoto, T. Katsufuji, T. Ishikawa, A. Urushibara, T. Arima, and Y. Tokura, Phys. Rev. Lett. **75**, 109 (1995); Y. Okimoto, T. Katsufuji, T. Ishikawa, T. Arima, and Y. Tokura, Phys. Rev. B **55**, 4206 (1997).
- <sup>5</sup> K. Takenaka, K. Iida, Y. Sawaki, S. Sugai, Y. Moritomo, and A. Nakamura, cond-matt/9810035 (unpublished).
- <sup>6</sup> S. G. Kaplan, M. Quijada, H. D. Drew, D. B. Tanner, G. C. Xiong, R. Ramesh, C. Kwon, and T. Venkatesan, Phys. Rev. Lett. **77**, 2081 (1996).
- <sup>7</sup> K. H. Kim, J. Y. Gu, H. S. Choi, G. W. Park, and T. W. Noh, Phys. Rev. Lett. **77**, 1877 (1996).
- <sup>8</sup> M. Quijada, J. Černe, J. R. Simpson, H. D. Drew, K. H. Ahn, A. J. Millis, R. Shreekala, R. Ramesh, M. Rajeswari, and T. Venkatesan, Phys. Rev. B **58**, 16 093 (1998).
- <sup>9</sup> J. A. Fernandez-Baca, P. Dai, H. Y. Hwang, C. Kloc, and S-W. Cheong, Phys. Rev. Lett. **80**, 4012 (1998).
- <sup>10</sup> J. H. Jung, K. H. Kim, D. J. Eom, T. W. Noh, E. J. Choi, Jaejun Yu, Y. S. Kwon, and Y. Chung, Phys. Rev. B **55**, 15 489 (1997).
- <sup>11</sup> K. H. Kim, J. Y. Gu, H. S. Choi, D. J. Eom, J. H. Jung, and T. W. Noh, Phys. Rev. B **55**, 4023 (1997).
- <sup>12</sup> G. C. Xiong, Q. Li, H. L. Ju, R. L. Greene, and T. Venkatesan, Appl. Phys. Lett. **66**, 1689 (1995).

- <sup>13</sup> J. H. Jung, K. H. Kim, H. J. Lee, J. S. Ahn, N. J. Hur, T. W. Noh, M. S. Kim, and J.-G. Park, Phys. Rev. B **59**, 3793 (1999).
- <sup>14</sup> J. H. Jung, K. H. Kim, T. W. Noh, E. J. Choi, and Jaejun Yu, Phys. Rev. B **57**, R11 043 (1998).
- <sup>15</sup> H. L. Liu, S. L. Cooper, and S-W. Cheong, Phys. Rev. Lett. **81**, 4684 (1998).
- <sup>16</sup> N. Furukawa, Y. Moritomo, K. Hirota, and Y. Endoh, cond-mat/9808076 (unpublished).
- <sup>17</sup> Y. Moritomo, A. Machida, K. Matsuda, M. Ichida, and A. Nakamura, Phys. Rev. B **56**, 5088 (1997).
- <sup>18</sup> There are still some debates on the origin of the 1.5 eV peak. Quijada *et al.* [Ref. 8] assigned it to an interatomic transition between the  $\text{Mn}^{3+}$  levels splitted due to the Jahn-Teller (JT) distortion. Machida *et al.* [Ref. 19] attributed it to an optical transition related to the JT clusters. Jung *et al.* [Ref. 14] assigned it to an intraatomic transition between JT split  $\text{Mn}^{3+}$  levels. More systematic studies are required to get a better understanding on the origin of the 1.5 eV peak.
- <sup>19</sup> A. Machida, Y. Moritomo, and A. Nakamura, Phys. Rev. B **58**, 12 540 (1998); A. Machida, Y. Moritomo, and A. Nakamura, Phys. Rev. B **58**, R4281 (1998).
- <sup>20</sup> Guo-meng Zhao (private communication).
- <sup>21</sup> It is known that the energy of a small polaron motion measured by optical techniques is about 4 time larger than the activation energy measured by transport measurements. If the 1.2 eV peak is the small polaron absorption peak, the activation energy determined by the transport measurements should be 0.3 eV. Refer to P. A. Cox, *Transition Metal Oxides*, (Clarendon Press, Oxford, 1992).
- <sup>22</sup> A. V. Boris, N. N. Kovaleva, A. V. Bazhenov, P. J. M. van Bentum, Th. Rasing, S-W. Cheong, A. V. Samoilov, and N.-C. Yeh, Phys. Rev. B **59**, R607 (1999).



- <sup>23</sup> K. H. Kim, J. H. Jung, and T. W. Noh, Phys. Rev. Lett. **81**, 1517 (1998).
- <sup>24</sup> According to the Ioffe-Regal criteria,  $l \sim a$  near metal-insulator transition. For the metallic state,  $l \gg a$ . Refer to *The Metallic and Nonmetallic States of Matter*, edited by P. P. Edwards and C. N. R. Rao (Taylor & Francis, London, 1985), Chapt. 2.
- <sup>25</sup> D. Emin, Phys. Rev. B **48**, 13 691 (1993).
- <sup>26</sup> S. Yoon, H. L. Liu, G. Schollerer, S. L. Cooper, P. D. Han, D. A. Payne, S-W. Cheong, and Z. Fisk, Phys. Rev. B **58**, 2795 (1998).
- <sup>27</sup> D. Louca, T. Egami, E. L. Brosha, H. Röder, and A. R. Bishop, Phys. Rev. B **56**, R8475 (1997).
- <sup>28</sup> K. H. Kim, J. H. Jung, D. J. Eom, T. W. Noh, Jaejun Yu, and E. J. Choi, Phys. Rev. Lett. **81**, 4983 (1998).
- <sup>29</sup> K. Kubo and N. Ohata, J. Phys. Soc. Jpn. **33**, 21 (1972).
- <sup>30</sup> H. Röder, J. Zhang, and A. R. Bishop, Phys. Rev. Lett. **76**, 1356 (1996).
- <sup>31</sup> J. E. Gordon, R. A. Fisher, Y. X. Jia, N. E. Phillips, S. F. Reklis, D. A. Wright, and A. Zettl, Phys. Rev. B **59**, 127 (1999).
- <sup>32</sup> J. J. Hamilton, E. L. Keatly, H. L. Ju, A. K. Raychaudhuri, V. N. Smolyaninova, and R. L. Greene, Phys. Rev. B **54**, 14 926 (1996).

## FIGURES

FIG. 1.  $\rho(T)$  of the NSMO single crystal. The solid and the dashed lines represent the resistivity curves of polished and annealed NSMO, respectively.

FIG. 2. (a)  $R(\omega)$  and (b)  $\sigma(\omega)$  for polished and annealed NSMO.

FIG. 3. (a)  $R(\omega)$  and (b)  $\sigma(\omega)$  for gold corrected and not corrected NSMO. In (b), the solid square denotes the value of dc conductivity.

FIG. 4.  $T$ -dependent  $R(\omega)$  of the annealed NSMO with gold correction.

FIG. 5.  $T$ -dependent  $\sigma(\omega)$  of the annealed NSMO with gold correction.

FIG. 6. Schematic diagrams for  $T$ -dependent  $\sigma(\omega)$  of the NSMO for (a)  $T > T_C$  and (b)  $T \ll T_C$ , respectively.

FIG. 7. Magnified  $\sigma(\omega)$  of NSMO up to 2.0 eV. The solid square, triangle, and circle represent the dc conductivity values at 15, 120, and 180 K, respectively. In the inset,  $\sigma(\omega)$  at 15 K are fitted with the simple Drude model.

FIG. 8.  $T$ -dependent  $N_{eff}$  (0.8 eV) of the NSMO single crystal. The solid line refers to the behavior of  $\gamma_{DE}(T)/\gamma_{DE}(0)$ .

















